

## Technical Data Sheet

Date of Issue 02/05/2018

Rev. 04\_21/05/2025

# T205

## Painter's Basic Masking Tape



### Product Description

Painter's Basic, medium adhesion masking tape characterized by a regular crepe paper backing and a natural rubber adhesive. Suitable for indoor applications, for masking operations in painting and building, and for non-critical bundling, holding, splicing, and labeling. Capable to exposure ultra-violet (UV) light for up to five hours. Recommended to be removed within 24 hours. FSC® and PEFC certified masking tapes available on demand.

### Features

- Medium adhesion
- Regular paper for masking operations
- Good holding power
- Clean removal in warm environments without breaking
- Good contact on multiple surfaces
- Good paint anchorage

### Main Applications

- DIY and Professional masking, painting and building operations (no UV exposure recommended)
- Non – critical bundling, splicing and holding
- Temporary labeling and marking activities

### Technical Data

|                          | Metric     | Imperial Units | Test Method         |
|--------------------------|------------|----------------|---------------------|
| Total weight*            | 80 g/m2    | 80 g/m2        | ISO 536             |
| Total thickness*         | 110 µm     | 4.3 mils       | Internal            |
| MD tensile strength*     | 37 N/cm    | 21.1 Lbs/in    | AFERA 5004/PSTC 131 |
| MD elongation at break*  | 7 %        | 7 %            | AFERA 5004/PSTC 131 |
| Adhesion to steel plate* | 1.9 N/cm   | 17.4 oz/in     | AFERA 5001/PSTC 101 |
| Service temperature      | up to 60°C | up to 140°F    |                     |

**Backing material**  
Saturated crepe paper

**Type of adhesive**  
Natural rubber

\*Typical value

### Available colour



### Technical Information and Product Use

All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. The accuracy or completeness of such information is not guaranteed. The technical information, suggestions and other statements contained in this document have been compiled for your guidance and usage. TTPL reminds the user of the products to make sure that the product is used as per the instructions and suggestions provided. It is the user's sole responsibility to determine the suitability of the product in actual application under specific conditions.

### Storage and Shelf Life

Suggested storage in dry area away from direct sunlight temperature should range from 59°F / 15°C to 77°F / 25°C with max relative humidity of 50%. Tape and jumbo roll should be used respectively within 12 months and 6 months from date of manufacture. TTPL does not take responsibility for the defective material if is not stored and used in accordance with the conditions listed above.